



TR INDUSTRIES
11022 Vulcan Street
South Gate, CA 90280-0893
Phone 562-923-0838 • Fax 562-861-3475
www.trmoldrelease.com • info@trmoldrelease.com

TR-102 REGULAR MOLD RELEASE

DESCRIPTION:

A high production paste wax mold release with excellent breakdown characteristics for fast, even coverage. A firm carnauba based mold release paste wax blended with other synthetic waxes for use in various thermo-set composite molding applications.

PRODUCT FEATURES:

- ★ High carnauba wax content polishes to high gloss without streaking
- ★ Good heat and chemical resistance properties
- ★ Easy application and wipe off characteristics
- ★ Reduced wax build up and styrene accumulation



PHYSICAL PROPERTIES:

Dry Time: 5-10 minutes @ 72°F. Varies depending on working temperature
Specific Gravity: .80-.82 (approx. 6.75lbs./Gal)
Wax Melting or Softening Point: 185 - 200°F (85 - 93°C)
Color: Off-white

USES:

- As a release agent for composite molding on all FRP tooling, metal and other hard surface molds.
- ★ Open mold hand or spray lay up
 - ★ Resin Transfer/injection (RTM) & (RIM)
 - ★ Vacuum bag and compression molding
 - ★ Polyester & epoxy resins

NOTE: Check suitability when heat curing or higher temperature molding above 200°F (93°C)

APPLICATION:

On new or reconditioned tooling, suggest use of our sealer glaze TR-301 or TR-910 semi-permanent sealer prior to waxing for added release, gloss and mold life. Apply wax with sponge applicator in thin even circular motion to the mold surface. Allow to haze dry (approx. 5-10 min) depending on ambient temperature and polish wipe to gloss finish with soft cloth (do not use microfiber cloth). For new or reconditioned molds, apply a minimum of 6 coats of paste wax, waiting approximately 30-60 minutes between applications for the wax to set & harden after the polish wipe. Best results are obtained, if after application, mold is allowed to stand overnight and a subsequent final coat of wax release applied the following day prior to gel coating. Follow with a coat of wax for the first 2-3 parts released. Then determine how many parts can be effectively produced before re-waxing is required. This will vary depending on molding condition, configuration, resin, mold cycles, effective cure of production gel coat and other factors.

STORAGE AND PRECAUTIONS:

Flammable solid, store in a cool dry place and keep in original unopened container. Keep away from spark, open flame or other sources of ignition.

PACKAGING:

Available in 14oz (397g) cans and packaged in case quantity of 12. Please contact your local TR distributor or call direct.

FOR INDUSTRIAL USE ONLY

The information contained herein is based on tests considered to be reliable and accurate. Because of the wide variance of associated materials and conditions, however no warranty is expressed or implied. Each user is encouraged to prepare a test part for their particular application.