

## Efka® PU 4063

Efka® PU 4063 is a polymeric wetting and dispersing agent for the deflocculation of inorganic and organic pigments in high-quality solvent-based pigment pastes. This results in:

- reduced dispersing time
- improved gloss
- prevention of flooding and floating
- higher color strength

### chemical nature

modified polyurethane

---

## Properties

### physical form

yellowish liquid

### storage

Efka® PU 4063 should be stored in a cool and dry place.

### typical properties (no supply specification)

density at 20 °C (68 °F)	~ 0.99 g/cm <sup>3</sup>
solids	~ 45%

---

## Application

Efka® PU 4063 is a dispersing additive for organic and inorganic pigments in high-quality solvent-based pigment pastes.

Efka® PU 4063 reduces the dispersing time and the mill base viscosity and thus facilitates the formulation of highly concentrated pigment pastes. After the pigment paste has been blended into paint, Efka® PU 4063 prevents flooding and floating of pigments and promotes excellent gloss and high color intensity.

Efka® PU 4063 is readily compatible with a wide range of binder types. Pigment pastes based on Efka® PU 4063 can therefore be used in 2-component polyurethane paints, 2 - component epoxy paints, unsaturated polyester, stoving paints and air-drying paints.

**recommended concentrations**

Calculation method for the required amount of Efka® PU 4063 (as supplied) based upon pigment:

inorganic pigments	15-20 % of weight
titanium dioxide	4-5 % of weight
organic pigments	30-60 % of weight
carbon blacks	80-100 % of weight

Efka® PU 4063 should be incorporated in the mill base before adding the pigments. Efka® PU 4063 should be blended with the pigments in the mill base. The optimal amount to be added to a given system must be determined by testing. Usually it is in the range from 1 to 5% relative to the inorganic pigments or 15 to 50% relative to the organic pigments.

## Contacts worldwide

## Asia

BASF East Asia Regional Headquarters Ltd  
45/F, Jardine House  
No. 1 Connaught Place  
Central Hong Kong  
China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

## North America

BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

## Europe

BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

## South America

BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

**Validity**

This Technical Data Sheet is valid for all versions of the Efka® PU 4063.

**Safety**

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

**Note**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)