

TEROSON EP 5055

May 2018

PRODUCT DESCRIPTION

Technology	Epoxy Resin
Additional Information	2-component solvent free toughend epoxy resin

TEROSON EP 5055 is a solvent free, two component adhesive, based on toughened Epoxy resins. The material has a very good adhesion to e.g.:

Application Areas:

It is special designed for bare steel, zinc coated steels and aluminum alloys used in the automotive industry or body repair shops, where high strength and corrosion protection properties are required.

TECHNICAL DATA

(Typical Test Results)

PART A

Base	Epoxy Resin
Colour	black
Density	approx. 1.0 g/ml
Viscosity	approx. 145 Pa.s
Measuring equipment	Physika UDS 200
Measuring system	plate/plate Ø 20 mm
Shear rate	10 s ⁻¹
Temperature	23 °C

PART B

Base	Amine
Colour	grey-green
Density	approx. 1.1 g/ml
Viscosity	approx. 75 Pa.s
Measuring equipment	Physika UDS 200
Measuring system	plate/plate Ø 20 mm
Shear rate	10 s ⁻¹
Temperature	23 °C
Mixing ratio A:B	
by volume	1:1

Mixture (PART A+B)

Colour	dark grey
Odour	almost without odour
Solids	100 %
Curing times	
initial strength	approx. 4 h at 23 °C
Shear strength (based on DIN EN 1465)	
final strength	approx. 2 d at 23 °C or 30 minutes at 100 °C
	object temperature
cured at ambient temperature	18 to 22 MPa

cured at elevated temperature	> 20 MPa
Peel test (DIN EN ISO 11339)	
Steel, 0.2 mm thick layer	>4 N/mm
(7 d at 23 °C, 50 % rh)	
E-Modulus	1,500 MPa

PRELIMINARY STATEMENT

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Application:

TEROSON EP 5055 is processed from universal cartridges with manual application tools (dispenser driven by hand, air pressure or battery). Only use dispensers that are equipped with a piston rod. Prior to screwing the static mixer, a small amount of the material should be pressed out to ensure that both components are passed on simultaneously. After mixing, the adhesive is ready for use and must be processed within 80 min, since viscosity increases when curing starts. In order to avoid the bonded parts being displaced, it is recommended that they should always be fixed during the process of curing. The processing time depends on the temperature.

Pretreatment:

The surfaces must be dry and free of oil, grease and dust. For pretreatment of the application area / surface use TEROSON VR 10. Grinding surface may improve adhesion, dependent on substrate.

After pretreatment we recommend on bare steel or bare aluminium a surface conversion with BONDERITE M-NT 1455-W.

Curing:

TEROSON EP 5055 cures without additional exterior heat only by chemical reaction after mixing component A and B at room temperature. Accelerated curing at 60 °C object temperature for 60 minutes is possible (e.g. infrared heaters).

Cleaning:

Fresh, uncured material can be removed with . Cured adhesive can only be removed mechanically.



Storage:

Frost sensitive	under certain conditions (may cristalize, reversible > 40 °C)
Recommended storage temperature	15 to 25 °C
Shelf life	12 months in original packaging

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3

