

Chemical/Physical Nature

ZC-196 resin is an unsaturated polyester resin with phthalic anhydride, maleic anhydride and standard glycol as the main raw materials. It has been dissolved in cross-linking monomers such as styrene and has high viscosity and medium reactivity.

Benefits and Application

ZC-196 resin has good strength and rigidity, fast post-curing, and good overall performance. It is suitable for ordinary fiberglass products.

FRP Typical Properties

Property	Value	Unit	TM
Barcol Hardness	64	-	GB/T 3584-2005
Flexural strength	300	Mpa	GB/T 1449-2005
Flexural modulus	17000	Mpa	GB/T 1449-2005
Tensile strength	320	Mpa	GB/T 1447-2005
Tensile modulus	16000	Mpa	GB/T 1447-2005

Application Guidelines

1. ZC-196 resin contains wax and does not contain accelerators and thixotropic additives.
2. If you have higher strength and toughness requirements, please contact sales directly.

Package

Net weight is 220 kg, metal barrel.

Liquid Resin Typical Properties

Property	Value	Unit	TM
Appearance	light yellow liquid	-	-
Acid value	20-26	mgKOH/g	GB/T 2895-2008
Viscosity, 25°C	0.7-0.8	Pa.s	GB/T 7193-2008
Solid content	62-68	%	GB/T 7193-2008
Thermal stability 80°C	≥24	h	GB/T 7193-2008
Gelation time 25°C	6-18	min	GB/T 7193-2008

Unfilled Castings Typical Properties

Property	Value	Unit	TM
Appearance	Qualified	-	-
Barcol Hardness	42	-	GB/T 3854-2005
HDT	60	°C	GB/T 1634-2004
Break elongation	2.5	%	GB/T 2567-2008
Tensile strength	60	Mpa	GB/T 2567-2008
Tensile modulus	3800	Mpa	GB/T 2567-2008
Flexural strength	120	Mpa	GB/T 2567-2008
Flexural modulus	3800	Mpa	GB/T 2567-2008

Zhongtritium(Changzhou) Technology Co.,LTD

Tel/WhatsApp/Wechat: +86 18136701732

Email: info@tritiumupr.com

web: www.tritiumupr.com

ADD: Room 807, Building 5, No 1590 longjin Road, Xinbei District, Changzhou, China

